



For Moderate Duty Horizontal and Vertical Drainage Applications

ArmorDrain 150 Protection/Drainage Dimple Board/Mat

Description

ArmorDrain 150 is a moderate duty impermeable polystyrene sheet that while under heat and pressure is formed into a dimpled drainage core. The core is then bonded to a single layer of a polypropylene filter fabric. The filter fabric retains soil and sand particles as well as freshly placed concrete or grout, allowing water to pass into the drainage core.

Purpose

ArmorDrain 150 is used as a protection and drainage roll and is engineered to provide ample strength to protect membranes against back fill soil and sediment and to provide excellent drainage capabilities.

Advantages

- Higher compressive strength for greater depth
- Strong resistance to hydrostatic pressure
- High flow dimpled drainage core
- Protects waterproofing membrane
- Easy installation

Leeds Data

ArmorDrain 150 Core is considered a GREEN product and can be used toward LEEDS building credits.

Prep/Application (With Membrane)

Application of waterproofing membrane should be completed.

Starting at a corner, install the ArmorDrain horizontally against the waterproofing membrane with the non-woven filter fabric side facing out-wards.

Extend the roll from the top of the footer to finished grade. When two edges come together from two separate rolls, overlap the dimples to create a continuous coverage of the wall.

For good adherence, **with** a membrane, apply uniform pressure throughout the surface area, not just the edges and corners. If needed, secure rolls to the wall using powder actuated mechanical fasteners.

For good adherence, **without** a membrane, mechanical fasteners or a suitable adhesive will be required to secure rolls to the wall. When using mechanical fasteners install top fasteners within the top 4" (102 mm).

If the roll overlaps the membrane once you have reached the grade line, a utility knife or similar tool can be used to cut the rolls to the correct height.

Backfilling/Drainage

Residential - Backfilling should begin no sooner than 24 hours after the installation of the board but must be backfilled within 30 days.

Sm11.23

Technical Data

Physical Properties	ArmorDrain 150 Values	Test Method
Core	Polystyrene	
Color	Black	
Dimple Height (Thickness)	.438" (11.13mm)	ASTM D1777
Compressive Strength	15,000 psf	ASTM D1621
Flow Capacity	16 g/min/ft-200L/min/M	ASTM D4716
Fabric	Polypropylene	
Flow rate	150 gal/min/ft ² (6110 L/min/m ²)	ASTM D4491
Geotextile grab tensile strength	110 lbs (50kg)	ASTM D4632
Geotextile elongation	60%	ASTM D4632
Geotextile puncture strength	65 psi	ASTM D4833
Geotextile apparent opening size (AOS)	100 US Sieve (.152mm)	ASTM D4751
Geotextile UV resistance @500 hrs	70% strength retained	ASTM D4355
Toxicity	Non-toxic, non-polluting	
Roll size/weight	4' x 50' (1.2 x 15.25m) 40 lbs. (18.1kg)	
Service life expectancy	>25 years (at pH between 4 and 9, and temperature below 77°F / 25°C) Do not expose to UV light for more than 30 days.	

www.Mar-flex.com 1-800-498-1411